



AB80

PROPERTIES

	UNIT	Own method based on :	R&D INFORMATION NO SPECIFICATION
Composition			A non-woven made of 100% polyester fibres.
Bonding			The product is mechanically bonded by needling.
Colour			white
Weight	g/m ²	ISO 9073-1	80 +/- 12
Thickness under ~ 0.5kPa	mm	ISO 9073-2	3 +/- 0.3 (measured before packaging and transport)
Tensile strength			
Machine Direction	N/5cm	ISO 9073-3	n.a.
Cross Direction	N/5cm	ISO 9073-3	n.a.
Elongation at Fmax			
Machine Direction	%	ISO 9073-3	n.a.
Cross Direction	%	ISO 9073-3	n.a.

ROLL DIMENSIONS

Standard Length	100Rm
Standard Width	150cm
Cardboard tube inner diameter	50mm

AEROVAC SYSTEMS LIMITED
Tel : +44 (0) 1274 550 500
Fax : +44 (0) 1274 550 501
E-Mail : sales@aerovac.com

AEROVAC SYSTEMES FRANCE
Tel : +33 (0) 5 61 37 89 89
FAX : +33 (0) 5 61 37 89 88
E-Mail : aerovac@aerovac.fr

AEROVAC ITALY S.r.l
Tel: +39 (0) 396 89 29 87
Tel: +39(0) 396 89 43 51
E-Mail: info@aerovac.it

All statements, technical information and recommendations contained in this publication are based on tests believed to be reliable, but their accuracy and/or completeness are not guaranteed. The user shall determine the suitability for this particular purpose and shall assume all risk and liability in correction herewith.